

PRODUCT : ZIRCONIUM SILICATE

BRAND : CER - ZIRCOMIN

<u>CHEMICAL PARAMETERS:</u>	<u>RANGE</u>
Zirconium as ZrO₂:	Min. 55.0 %
Hafnium as HfO₂:	Max. 2.0 %
Silica as SiO₂:	Max. 39.0 %
Alumina as Al₂O₃:	Max. 2.0 %
Iron Oxide as Fe₂O₃:	Max. 0.15 %
Titanium Oxide as TiO₂:	Max. 0.70 %
Loss on Ignition @ 1000°C:	Max. 2.25 %

<u>GRANULOMETRY</u>
Particle Size D(50)= 2.0 +/- 0.1 Micron

ORIGIN: Australian origin sand processed in UAE
PAKING: JUMBO BAGS/ 25 KGS/40 KGS HDPP BAGS